SUBLISTOP

NO DYE SUBLIMATION

The sublistop-transfer offers a **perfect degree of opacity on all coloured textiles** and meets the highest demands regarding **colour-fastness** and **durability**. In particular with **white transfers** on sportswear made of polyester or with a polyester content the **dye particles of the fabric** may **penetrate** into the transfer during the printing process or after some time. When producing a sublistop transfer, a **silver migration barrier** is put in a multi-layer procedure between the glue and the layer of dye, which prevents the dye of the fabric from running into the transfer.

The **main difference** between Sublistop and D3000 is the **silver migration barrier to avoid dye sublimation. This is in particular necessary for fabrics mainly made of polyester polyamide fibres.**

The sublistop-transfer is not suitable for softshell.



INFORMATION **TEXTILES** REOUIREMENTS APPLICATION cotton, cotton mix, minimum line width temperature: 160-170°C Preheating is not necessary synthetics positive: 1 mm, negative: 1.2 mm time: 10-15 seconds especially suitable for (feed) polyester fabrics in bright pressure: 0.5-0.8 kp/cm² colours vector file 3-4 bar (strong pressure) or pixel graphics with (jerseys, running shirts 600 dpi and bike shirts) strip off carrier foil while warm/hot not suitable for softshell minimum quantity 50 pcs. CARE CERTIFICATE SHELF LIFE $\langle\!\!\langle\!\rangle$ Ő washable up to 40°C tested for harmful approx. 6 months substances if kept airtight iron inside out in a dark environment Oeko-Tex Standard 100 Class 1 do not chlorinate suitable for babies do not tumble-dry and toddlers do not dry-clean